



EULL'S MANUFACTURING CO INC

3187 LABEAUX AVENUE NE

St. Michael, MN 55376

P: 763-497-2742

F: 763-497-4634

www.eullsmfg.com

Vibra Press Roof Paver Specification Sheet

	<u>Value</u>	<u>Test Method</u>
Compressive Strength:	6000 psi	ASTM C 140
Dimensional Tolerance:	1/8 Inch	
Absorption:	5% Average	ASTM C 140
Freeze Thaw:	1% Max Loss (50 Cycles)	ASTM C 67

24" Diamond Face Specification Sheet

Plain Paver

Compressive Strength Average:	9,000 PSI
Dimensional Tolerance:	1/8 Inch
Absorption:	4% Average
Freeze Thaw:	1% Max Loss
Weight Per SQ Foot:	22 LBS

EULL'S MANUFACTURING SPLASH PANS

MIX DESIGN	MNDOT 3Y43
AIR CONTENT:	5%-8%
COMPRESSIVE STRENGTH	4,300 PSI

*** This document is not a warranty***

Quality you Can Depend On...Strength You Can Build on